



**NCFI Polyurethanes**

**Div. of Barnhardt Manufacturing Co.**

**PO Box 1528 • Mount Airy, NC 27030**

**800-346-8229**

**www.NCFI.com**

## 21-070 Rigid Pour Foam System

### Technical Data Sheet

NCFI 21-070 is a two component, HFO blown, low GWP, all PMDI based, pour-in-place urethane rigid foam system. It is designed for void filling applications which require a high degree of flow.

### Typical Properties of Components

Component	B-21-070	A2-000
Appearance	Brown liquid	Brown liquid
Brookfield Viscosity @ 20 rpm	450 cps at 72°F	200 cps at 72°F
Specific Gravity	1.13	1.24
Storage Temperature	40°F - 90°F	40°F- 90°F

### Mix Ratio

By weight..... 100 parts B : 112 parts A  
 By volume..... 100 parts B : 100 parts A

### Typical Properties of Mixed System at 72°F

	Regular	Fast
Cream Time	45 seconds	18 seconds
Gel Time	230 seconds	120 seconds
Tack Free Time	360 seconds	180 seconds
Rise Time	400 seconds	220 seconds
Free Rise Core Density	2.2 pcf	

The Information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained there from. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the sole responsibility of the user. NCFI Polyurethanes shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond NCFI's direct control. NCFI MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendations, nor as an inducement to practice any patented invention without permission of the patent owner.

## Typical Physical Properties

---

<b>Overall Molded Density</b>	<b>3.2 pcf</b>
<b>Compressive Strength</b>	<b>30.1 psi</b>
<b>Initial k-factor</b>	<b>0.167</b>
<b>Moisture Vapor Transmission</b>	<b>2-3 perm inch</b>
<b>Closed Cell Content</b>	<b>90%</b>
<b>Water Absorption</b>	<b>0.044 lb/ft<sup>2</sup></b>
<b>Flammability</b>	
<b>UL-94 HBF</b>	<b>Pass</b>
<b>FMVSS-302</b>	<b>Pass</b>
<b>FAR 25.853a(ii)</b>	<b>Pass</b>
<b>Resistance to Solvents</b>	<b>Excellent</b>
<b>Resistance to Mold &amp; Mildew</b>	<b>Excellent</b>
<b>Maximum Service Temperature</b>	<b>200°F</b>

\*The above values are average values obtained from laboratory experiments and should serve only as guide lines.

## Other Properties

---

- Meets Title 46 CFR 179.240 for flotation foam
- Meets USCG Title 33, Chapter 1, Part 183

## Storage and Handling

---

Store the poly from 65°F to 85°F. Avoid moisture contamination during storage, handling, and processing. For both components, pad containers and day tanks with either nitrogen or dry air (desiccant cartridge or air dryer @ -40°F dew point). For optimum shelf life, the recommended storage temperature for iso is 64°F to 86°F. **Do not expose iso to lower temperatures – freezing may occur.** Shelf life is 6 months for factory sealed containers.

Original: 042517  
 Modified: 112817  
 Modified 2: 121917  
 Modified 3: 010218  
 Modified 4: 022819  
 Modified 5: 053019